



Evolution

Ficha técnica

Aplicaciones - Applications - Anwendung - Applications	Gardens - Terraces - Trade Fairs - Swimming Pool Surroundings
Fibra - Fibre - Faser - Fibre	100% polyethylene monofilament + 100% polyethylene curly
Fabricación - Production - Produktion - Fabrication	Tufting
Calibre - Gauge - Teilung - Jauge	3/8 inch
Puntadas - Stitches - Stichzahl - Noeuds	ca. 18 / 10 cm
Tufts - Tufts - Noppenzahl - Touffes	ca. 18.900 / m ² ± 10%
Altura de la fibra - Pile height - Polhöhe - Hauteur de la fibre	ca. 35 mm
Peso de la fibra - Pile weight - Polgewicht - Poids de la fibre	ca. 1.924 gr / m ² ± 10%
Peso total - Total weight - Gesamtgewicht - Poids total	ca. 3.064 gr / m ²
Refuerzo primario - Tuft cloth - Tufttuch - Dossier primaire	Double Polypropylene, ca. 240/sqm
Refuerzo secundario - Backing - Rücken - Dossier secondaire	Latex (DOW)
Relleno - Infill - Verfüllung - Remplissage	Bottom layer composition: Washed and dried silica sand (90% round); Top layer composition: recycled rubber granules (option)
Color - Colour - Farbe - Couleur	Green
Ancho del rollo - Roll width - Rollbreite - Largeur des rouleaux	200 / 400 cm
Largo del rollo - Roll length - Rolllänge - Longueur des rouleaux	20 m
Solidez del color - Light fastness - Farbechtheit - Tenue des couleurs	Scale 7 (DIN 54004)
Estabilidad a los rayos UV - UV Stability - UV Stabilität - Stabilité à la radiation UV	> 8.000 hours UV-A (DIN 53387)



Forma del hilo
Forma "I"



Garantía del producto
(años)